

SPECIFICA TECNICA	
TC92535 MONTANTE SINTETICO per VETRINI metodo con Isoparaffina	
REV. 3 DEL 30/04/2026	Metodo controllo MC92535

Nome prodotto	MONTANTE SINTETICO per VETRINI metodo con Isoparaffina	
Codice prodotto	TC92535	
Composizione	Miscela di resina acrilica termoplastica in solvente isoparaffinico, densità a 20°C = 0,889 g/l	
SPECIFICHE TECNICHE		
Aspetto	Liquido incolore	
Viscosità	970 - 1030 cP	
Indice di rifrazione	1,430 - 1,450	
Idoneità all'uso	Montante sintetico universale	
Scadenza	4 anni dalla produzione in confezione integra	
DOCUMENTO EMESSO A MEZZO COMPUTER E PERTANTO NON FIRMATO		

TECHNICAL DATA SHEET	
TC92535 SYNTHETIC MOUNTING MEDIUM for SLIDES method with Isoparaffin	
REV. 03 – 30/04/2026	Control method MC92535

Product name	SYNTHETIC MOUNTING MEDIUM for SLIDES method with Isoparaffin	
Product code	TC92535	
Composition	Mixture of thermoplastic acrylic resin in isoparaffinic solvent, density at 20°C = 0.889 g/l	
TECHNICAL SPECIFICATIONS		
Appearance	Clear, colorless liquid	
Viscosity	970 – 1030 cP	
Refractive Index	1,430 – 1,450	
Suitability for use	Universal synthetic mounting	
Expiry date	4 years from production in tightly closed bottle	
THIS DOCUMENT HAS BEEN MADE BY ELECTRONIC DATA PROCESSING AND THEREFORE NOT SIGNED		